

TECHNICAL DATA SHEET



Product name	Revised
GENAN COATED TOP LAYER CRIMSON RED	01.05.2022

Product description
Free-flowing, homogeneous and uniform rubber granulate, derived from end-of-life tyres through granulation and cleaning - and colour-coated with inert, non-toxic pigments and polyurethane binder.

Contact Data of Manufacturer						
Plant:	Genan A/S Jøgendøvej 16 DK-8800 Viborg Denmark	Genan GmbH Gottlieb-Daimler Straße 34 D-46282 Dorsten Germany	Betriebsstätte Oranienburg: Birkenallee 80 D-16515 Oranienburg Germany	Betriebsstätte Kammlach: Im Gewerbepark Unterallgäu 1 D-87754 Kammlach Germany	Genan, S.A. Lugar da Pardala Estrada Nacional 109, Km 31 PT-3880-728 São João de Ovar Portugal	Genan Inc. 18038 Beaumont Hwy. Houston TX77049 USA
Tel:	+45 8728 3000	+49 2362 9527 0	+49 3301 578 0	+49 8261 7369 0	+351 256 580 600	+1 713 6748500
Fax:		+49 2362 9257 150	+49 3301 578 150	+49 8261 7369 150		+1 713 6748501
E-mail:	info-dk@genan.com	info-de@genan.com			info-pt@genan.com	info-us@genan.com

Typical properties				
Properties	Test methods	Unit	Specification	Typical values
Specific density	ASTM D1817-05(2016)	kg/m ³	1.100-1.200	1.160
CIELAB colour code (Note 2)	EN ISO 11664-4 "Colorimetry - Part 4: CIE 1976 L*a*b* Colour space"	n/a	L*: 25,00 a*: 21,00 b*: 10,00 ΔE < 3	L*: 25,00 a*: 21,00 b*: 10,00 ΔE < 2
Bulk density	EN 1097-3:1998	kg/m ³	495 ±8%	495
Particle size range	ISO 13322-2:2006	mm	2,0-4,0	2,0-4,0
Total polymer content (RCH)	ISO 9924-3:2009	%	> 40	45
Ash content	ISO 9924-3:2009	%	< 15	8
Moisture content (Loss: 2h @ 105°C)	ASTM D1509 - 15	%	< 1	< 1
Free metal content	OA-698; (Note 1)	%	< 0,004	< 0,002
Free fibre content	OA-698; (Note 1)	%	< 0,002	< 0,001
Other contamination	OA-698; (Note 1)	%	< 0,004	< 0,002
Inhalable dust classification	EN 15051-2:2013+A1:2016		Very low to low	Very low
PAH 8 REACH	AfPS GS 2019:01 PAK	mg/kg	< 20	< 15

Note 1: Non-standardized test method "Determination of bulk density and free impurities in rubber powder and granulate", which your Genan representative will forward upon request. This test method is chosen as values obtained from the use of ASTM D5603 are below the detection limits.

*Note 2: L*a*b* colour code defined with an annually calibrated Konica Minolta CM5 spectrophotometer.*

Remarks	
DIN 18035-7:2019	GENAN COATED TOP LAYER complies with all requirements in relation to migration according to DIN 18035-7:2019.
EN 71-3:2019	GENAN COATED TOP LAYER complies with all requirements according to EN 71-3:2019_Safety of Toys - Part 3: Migration of certain elements.
PAH 8 REACH	A material sample has been extracted in accordance with EN 17409:2019, and the result is presented as a moving average of the 4 most recent analyses.
Particle size distribution	Information on the actual particle size distribution is available on the relevant sieve curves, which may be downloaded from the Genan website at any time.
Abrasion resistance	GENAN COATED TOP LAYER is a colour-coated product. As friction will cause colour-coating wear-off, it should be anticipated that the product will gradually lose its colour during use. Do not apply chemicals and/or abrasives, as such products will result in the fading or rub-off of the colour-coating. Take note that colour may rub off onto clothing, shoes or similar items.
Health & Safety	Guidelines on health and safety are stated in the relevant Safety Data Sheet, which may be downloaded from the Genan website at any time.

Characteristics stated are typical for the product. The product is derived from a large number of different tyres; consequently, Genan cannot give any exact values on the chemical composition of the material. The above-mentioned characteristics and values have been prepared to the best of our knowledge, and Genan shall not be liable for any insufficiency or inaccuracy in such information.

CERTIFICATIONS	Genan A/S	Genan GmbH	Genan Inc.	Genan, S.A.
	ISO 9001:2015	ISO 9001:2015	ISO 9001:2015	ISO 9001:2015
	ISO 14001:2015	ISO 14001:2015	ISO 14001:2015	ISO 14001:2015
	ISO 45001:2018	ISO 45001:2018	ISO 45001:2018	ISO 45001:2018
	ISO 50001:2018	ISO 50001:2018	ISO 50001:2018	ISO 50001:2018